

Technical Data Sheet

Revision Date: 2020-11-15 Name: WANNATETM HT-100

NO. PCS_0005 Version: 7.0

Application

WANNATETM HT-100 (1,6-hexamethylene diisocyanate based polyisocyanate) is a solvent free aliphatic polyisocyanate based on hexamethylene diisocyanate (HDI), colorless to slightly yellowish clear liquid.

Equivalent Weight	~ 193
Density at 25 °C	$\sim 1.16 \text{ g/cm}^3$

WANNATETM HT-100 can be used as the hardener component for lightfast two-component polyurethane coatings with high resistance to chemicals and weathering, very good gloss retention and outstanding mechanical properties. Preferred co-reactants are polyacrylates or polyester polyols.

The main applications for coatings based on WANNATETM HT-100 are automotive refinishing, transportation, industrial finishing and plastics.

Properties	Unit	Specification
NCO Content	%	21.70 ~ 22.20
Viscosity at 25 °C	mPa s	1750 ~ 3250
Chromatic Number	АРНА	\leq 40
HDI Content	%	\leq 0.2

Specification

Package(s)

20 kg	Metal drum

60 kg Metal drum



220 kg

Metal drum

IBC & ISO TANK

Other packages available according to customer needs

Storage / Solubility

Storage in original container. Protect from moisture, heat and foreign material.

WANNATETM HT-100 is sensitive to moisture. Storage at higher temperatures may result in increasing of color and viscosity.

WANNATETMHT-100 can be thinned with esters, ketones and aromatic hydrocarbons such as ethyl acetate, butyl acetate, methoxypropylacetate, acetone, methyl ethyl ketone, methyl isobutyl ketone, cyclohexanone, toluene, xylene, solvent naphtha 100 and mixtures thereof. Generally speaking, it has good compatibility with the solvents listed. However, the solutions formed must be tested for their storage stability. Only PU grade solvents should be used (max.0.05% water, absence of reactive groups such as hydroxyl or amino groups). Aliphatic hydrocarbons are unsuitable as solvents.

WANNATETM HT-100 is not recommended to be thinned to a lower solid content. Prolonged storage of a solution with a lower content may result in turbidity or sedimentation, even gelation.

Compatibility

WANNATETM HT-100 can be mixed with the following products: aliphatic polyisocyanates, polyester polyols, aromatic polyisocyanates and polyacrylates.

Shelf Life

WANNATETM HT-100 is sensitive to moisture and must be stored in tightly sealed container. It can be stored for at least 15 months at temperatures between 0 and 30 $^{\circ}$ C.

For more information about safety and environment, please refer to our MSDS or contact our customer service center.



The information provided here is for reference only. The specification will be provided in the quality certificate or in the contract. It is the user's responsibility to test the material and its suitability for a process. We have no control over what another party does with the material and we cannot take any responsibility for another party's action. Nor will we be responsible for any indirect damages while using our products. The user is welcome to contact our customer and technical service center with questions on our products.